

Amendments to the Specification:

Please amend the specification at p. 8, table as follows:

Permeability to gases (cm ³ /m ² - 24h, - bar, at 75% relative humidity)			Permeability to water vapor (g/cm² - 24 h g/m ² - 24 h at 20°C - 85% relative humidity)	Temperature resistance (°C)	Sealing temperature (°C)
Oxygen	Carbonic anhydride	Nitrogen			
4 to10	12 to 30	1.3 to 5	1.0 to 1.6	-60 to +100	+130 to +200